

Sichuan Dowhon International Co.,Ltd.

FVMQ --Selection Guide

Grade Name	Density /g/cm ³	Hardness /Shore A	Tensile Strength /MPa	Elongation /%	Tear Strength /kN/m	Compression Set /%
General Grade						
DHFS-G1040	1.44	39	9.8	510	28	9
DHFS-G1050	1.46	51	9.5	380	26	9
DHFS-G1060	1.48	60	9.1	325	24	8
DHFS-G1070	1.48	70	8.5	230	17	7
DHFS-G1080	1.48	80	8.2	200	17	7
High Tear Resistance						
DHFS-1040MT	1.44	39	10	565	38	15
DHFS-1050MT	1.47	48	9.8	500	40	23
DHFS-1060MT	1.48	58	9.5	470	40	21
DHFS-1070MT	1.48	69	9.3	355	38	23
DHFS-1080MT	1.48	78	9.5	320	32	23
Good Adhesiveness						
DHFS-Z1040	1.45	40	8.7	400	16	10

ADD:Room 2010, 4 cell ,Fortune Center, No.191,Tongyi Bystreet
Chengdu,China P.S.: 610036

Tel/Fax:0086 28 8757 8925 Website: <http://www.dowhon.com> Email: twang@dowhon.com

****Profession makes delicate quality,innovation shapes industry future****

Sichuan Dowhon International Co.,Ltd.

DHFS-Z1060	1.46	60	9.1	328	20	9
DHFS-Z1070	1.47	70	8.5	320	16	9
Extrusion Grade						
DHFS-E1050	1.45	50	9.5	383	15	9
DHFS-E1060	1.46	60	10	370	19	8
DHFS-E1070	1.47	70	10	360	20	8
DHFS-E1080	1.48	80	10	350	20	7